

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 11/18, C08L 61/04, B43K 5/00		A1	(11) International Publication Number: WO 95/11283 (43) International Publication Date: 27 April 1995 (27.04.95)
(21) International Application Number: PCT/US94/11842 (22) International Filing Date: 17 October 1994 (17.10.94) (30) Priority Data: 139,225 18 October 1993 (18.10.93) US (60) Parent Application or Grant (63) Related by Continuation US 139,225 (CON) Filed on 18 October 1993 (18.10.93) (71) Applicant (for all designated States except US): THE GILLETTE COMPANY [US/US]; Prudential Tower Building, Boston, MA 02199-4099 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): LIN, Nan-Jae [US/US]; 6 Shea Circle, Burlington, MA 01803 (US). KLASSMAN, Andrew, R. [US/US]; 5 Margaret Road, Sharon, MA 02067 (US). NICOLL, Roy [GB/GB]; 52 Reynards Close, Winkersham, Wokingham, Berkshire RG11 5NU (GB). PACKHAM, Charles, Christopher [GB/GB]; 35 Old Wokingham Road, Crowthorne, Berkshire RG11 6SS (GB). HULSE, Vliet [US/US]; 1 Bristol Drive, Duxbury, MA 02332 (US).		THOMPSON, John [US/US]; 81 Pine Street, Medfield, MA 02052 (US). (74) Agents: HANDELMAN, Joseph, H. et al.; Ladas & Parry, 26 West 61st Street, New York, NY 10023 (US). (81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ).	
(54) Title: LIQUID INK (57) Abstract A non-erasable liquid ink for a marking instrument including a colorant and a solvent and having a water content of about 0-15 % by weight and a viscosity of about 15 to 4,500 cps. Also disclosed is a marking instrument filled with an ink of such a viscosity or lower in its reservoir.		Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

LIQUID INK

The present invention relates to liquid inks. More particularly, it relates to liquid inks for marking instruments.

5 Marking instruments, e.g., pens and markers, have a tip to which a liquid ink is supplied from a reservoir to be applied onto a substrate, such as a sheet of paper, by means of the tip which is moved over the surface of the
10 substrate to leave a liquid trace.

Traditionally, liquid inks for marking instruments either have a viscosity of about 5 centipoise ("cps") or lower (e.g., for fiber tip pens or fountain pens), or have a viscosity of
15 about 7,500 cps or higher (e.g., for ball point pens). The latter usually contain a certain amount of a polymeric material(s).

One of the features of the present invention involves non-erasable liquid inks for
20 marking instruments with a distinctive range of viscosity.

Thus, one aspect of the invention relates to a non-erasable liquid ink, with a water content of about 0-15% by weight, for a
25 marking instrument. By "erasable ink" is meant an ink, which, after being deposited on a porous substrate, cannot be erased using a conventional

- 2 -

rubbery eraser. The non-erasable ink includes a solvent and a colorant, e.g., a dye or a pigment, dissolved or dispersed in the solvent, and has a viscosity of about 15 to 4,500 cps.

5 More preferred ranges of viscosity include, but are not limited to, about 50 to 2,000 cps, about 100 to 1,000 cps, or about 150 to 600 cps. The viscosity of an ink of this invention described herein is that measured at a shear rate of 300
10 sec^{-1} at room temperature. The liquid ink may also contain one or more polymers with averaged molecular weights ranging from about 1×10^4 to 1×10^6 daltons (preferably, about 1×10^5 to 6×10^5 daltons) with the total content of the
15 polymer(s) being about 0.05% to 2.5% by weight of the ink. A more preferred range of the total polymer contents is about 0.05% to 1.0%. It is particularly preferred that the total polymer content be about 0.3%. Examples of suitable
20 polymers include, but are not limited to, polyvinylpyrrolidone ("PVP") and ketone/formaldehyde resin.

Preferably, one or more lubricants, such as oleic acid or oleic diethanolamine
25 ("ODEA"), can be incorporated in the liquid ink as to decrease friction resulting either from contact between a marking instrument and the substrate (e.g., paper) onto which a marking is being made, or, in the case of a ballpoint pen,
30 from contact between the roller ball and the socket, thereby enhancing smoothness in using the marking instrument.

The colorant used in the liquid ink may be either a dye (i.e., which can be
35 dissolved in a solvent), or a pigment (i.e., which can only be dispersed, rather than dissolved, in a solvent). When a pigment is

- 3 -

used, it is preferred that a gelling agent be also included in the ink so as to prevent pigment sedimentation or ink leakage.

Another aspect of this invention
5 relates to a non-erasable liquid ink, with a water content of about 0-15% by weight, for a marking instrument which includes (i) one or more polymers with averaged molecular weights ranging from about 1×10^4 to 1×10^6 daltons,
10 preferably, about 1×10^5 to 6×10^5 (e.g., PVP or ketone/formaldehyde resin), (ii) a colorant, and (iii) a solvent, with the total content of the polymer(s) being about 0.05% to 2.5% by weight (more preferably, about 0.05% to 1% by weight)
15 of the ink. In a particularly preferred embodiment, the total polymer content is about 0.3% by weight. Similarly, whenever necessary, other ingredients, such as a lubricant or a gelling agent, can also be included in the ink.

20 Note that a colorant incorporated in an ink of this invention does not include a colored polymer, e.g., polymeric dyestuff. Similarly, a polymer used in this invention is, by definition, not colored. By "polymer" is
25 meant a macromolecule consisting essentially of repeating units with a molecular weight of at least 1×10^4 daltons. A preferred M.W. range is about 1×10^4 to 1×10^6 daltons. A particularly preferred M.W. range is about 1×10^5 to 6×10^5
30 daltons.

Also within the scope of this invention is a marking instrument which includes: a body, a reservoir chamber within the body, and a liquid ink in the chamber. The
35 liquid ink may be an ink of the present invention as described above, or an ink of a lower viscosity which is most suitable for use

- 4 -

in fiber tip pens or fiber tip highlighters.

Preferably, the marking instrument further includes an ink feed device having a channel for conducting the ink from the chamber to a marking tip, an elastomeric member which partly confines the chamber and supports the feed device with respect to the body, and a valve defined by the feed device and the elastomeric member for controlling communication between the chamber and the channel, whereby the feed device is retractable relative to the body under a force exerted against the tip, and in response to such retraction the chamber is pressurized by deflection of the elastomeric member and the valve is opened to allow the ink to enter the channel from the chamber. Note that the marking instrument constructed in a manner described above may be equipped with a variety of different marking tips (e.g., a roller ball) and is not limited to any particular type of tip.

A further aspect of the present invention relates to a method of making a marking on a substrate, e.g., a piece of paper. The method includes the steps of: providing one of the above-described liquid inks of this invention, and applying the liquid ink against a surface of the substrate forming a marking.

One feature of the invention is the use of the valved ink feed device which allows lower viscosity ink to flow to the marking tip only when the tip is pressed against a writing surface. Without this valve restricting flow to the tip, the lower viscosity ink would tend to leak from the marking tip. By use of this valved ink feed device, lower viscosity ink can now be used, the ink having lower writing

- 5 -

friction when applied.

Other features and advantages of the present invention will be apparent from the following drawings and description of the preferred embodiments, and also from the
5 appending claims.

The drawings are first briefly described.

Figure 1 is an axial cross-section
10 through a forward end portion of a fiber tip pen according to an embodiment of the invention, the valve being shown in a closed condition;

Figure 2 is a view corresponding to Figure 1 but with the valve shown open;

15 Figure 3 is a longitudinal cross-section through a forward end part of a fiber tip highlighting marker in accordance with another embodiment of the invention, the valve being shown closed;

20 Figure 4 is the fiber tip marker of Figure 3 with the valve opened; and

Figure 5 is a marking tip of this invention with a roller ball.

Colorants to be used to prepare a
25 liquid ink of this invention can either be dyes or pigments. Examples of dyes include, but are not limited to, Solvent Blue 38, Solvent Violet 8, Basic Blue 7, Solvent Red 125, and Solvent Black 46. On the other hand, Pigment Blue 6,
30 phthallo Blue, Pigment Blue 15.2 and Carbon Black are examples of pigments. More than one dye or pigment can be used in a liquid ink to obtain the desired color, shade and the like. The viscosity of a liquid ink can also be "fine-
35 tuned" by varying its dye content.

Selection of solvents depends on, among others, the dyes or pigments to be used.

- 6 -

Solvents suitable for preparation of liquid inks include, but are not limited to, diethylene glycol monoethyl ether, phenyl cellosolve, ethylene glycol phenyl ether, dipropylene glycol and octylene glycol. As an example, diethylene glycol monoethyl ether can be used to dissolve Solvent Blue 38. Pigments, on the other hand, can be dispersed in solvents by techniques well known in the art, such as using high shear mixing equipment. Of note, solvents with low volatility (e.g., boiling point higher than 180°C.) and high hygroscopicity are preferred. Also note that more than one solvent can be included in a liquid ink either to improve the solubility of a dye or the dispersion of a pigment, or to "fine-tune", the viscosity of the ink.

However, a more drastic adjustment of viscosity is achieved by incorporating in a liquid ink one or more polymers having averaged molecular weights ranging from about 1×10^4 to 1×10^6 daltons. Examples of such polymers include, but are not limited to, PVP and ketone/formaldehyde resin. Note that PVP does not only confer viscosity on a liquid ink, it also serves as an elasticizer. By "elasticizer" is meant an ingredient in a liquid ink which makes the ink less likely to build up undesirably at the marking tip of a marking instrument during use. Whenever necessary, a proper elasticizer, regardless of its molecular weight, can also be incorporated in a liquid ink to reduce or eliminate buildup.

Also can be included in a liquid ink of this invention is a lubricant, such as oleic acid or oleic diethanolamine, to reduce the friction which is generated from contact between

- 7 -

a marking instrument and the substrate on which a marking is being made or between the ball and the socket of a ballpoint pen, as well as to prevent hard starting.

5 When a pigment is used to prepare a liquid ink, a gelling agent may also be included in the ink so as to prevent pigment sedimentation or ink leakage. A gelling agent is added to a liquid ink to provide the ink with an yield
10 point and to make the ink shear thinning, thus retard the sedimentation of pigment.

 The liquid ink of this invention is most suitable for use in a marking instrument having a feed device which conducts marking
15 liquid from the reservoir chamber to the marking tip supported by an elastomeric diaphragm which partly confines the reservoir chamber and forms a valve with the feed device so that, when the tip is applied against a surface, the feed
20 device retracts causing the diaphragm to pressurize the liquid in the reservoir and open the valve whereby liquid is pumped to the tip.

 For examples of such a "diaphragm valve" assembly, we refer to International
25 Publication No. WO 93/05966 (publication date: April 1, 1993). Figures 5, 6, 7, 8 and 14 of the referenced PCT application have been included in the drawings herein as Figures 1, 2, 3, 4 and 5, respectively.

30 Shown in Figures 1 and 2 herein is a fiber tip pen. A washer 6 is held in a barrel 1 by a nose cone 25 fitted in the forward end and having an axial bore in which a cylindrical piston 26 is accommodated. Extending through a
35 piston is a fiber rod 27 with a free end

- 8 -

protruding through the leading end of the nose cone to define a writing tip. The ports 16 in the valve sleeve 15 serve to deliver ink from the reservoir chamber to the rear end of the fiber rod when the valve is opened by a force exerted on the writing tip causing the feed assembly consisting of the fiber rod, piston and valve sleeve to retract and the washer 6 to flex, as shown in Figure 2.

10 Illustrated in Figures 3 and 4 herein is a fiber tip highlighter. The washer 6 is trapped within the forward end of the barrel 1 by a tubular nose piece 30 fitted to the barrel. A fiber core 33 is located within the nose piece and includes a head portion which is slidably guided relative to the nose piece by a bearing 34, the free end of the head being arranged to protrude from the nose piece and being shaped to define a broad edge for laying down a wide line of marker fluid. The rear end of the core bears on the central region of the washer 6 and is recessed to accommodate a central tube defining a feed channel 14 and the valve sleeve 15 surrounding the tube. When the marker tip is pressed against a surface, the core 33 retracts and causes the elastomeric washer 6 to flex rearwardly so that the valve is opened and the reservoir chamber is pressurized, whereby fluid is supplied to the core via the ports 16 and feed channel 14 and flows along the ducts in the core to the tip to be laid down thereby.

30 Shown in Figure 5 is a roller ball tip assembly which may be fitted into the sleeve of the pens similar to those shown in Figures 1 and 3. A ball housing 65 is telescoped together

- 9 -

with a feed rod 66 within a tubular case 67.
The feed rod has an axial bore 68 which conducts
marker fluid to the ball 69. As shown a small
secondary reservoir 70 is defined by the ball
housing immediately behind the ball, but this
may not be needed or could be given a greater
volume if required.

The two working examples set forth
below are to be construed as merely
illustrative, and not limitative of the
remainder of the disclosure in any way
whatsoever. A total of eleven different liquid
inks of this invention, i.e., Formulations 9-1,
9-2, 9-3, 9-4, 9-5, 9-6, 10-1, 11-1, 11-2, 11-3
and 13-1 as shown in Tables 1-4, were prepared
in the two working examples. Formulations 9-0
and 10-0 as shown in Tables 1-3, on the other
hand, are both prior art liquid inks.

Code names and abbreviations used in
Tables 1-4 denote the following solvents, dyes,
polymers and lubricants:

PM 71:	diethylene glycol monoethyl ether, from Ashland Chemical, Dublin, OH
PM 78:	phenyl cellosolve, from Ashland Chemical, Dublin, OH
PM 74:	oleic acid, from Henbel Emery Group, Hoboken, NJ
PM 83:	dipropylene glycol, from Ashland Chemical, Dublin, OH
PM 81:	polyvinylpyrrolidone PVP K-90 (averaged M.W. 3.6×10^5), from BASF, Parsippany, NJ
PM 21:	Solvent Blue 38, from the Gillette Co., Boston, MA
PM 24:	Solvent Violet 8, Neptun Violet Base,

- 10 -

from BASF, Parsippany, NJ
PM 25: Basic Blue 7, Basconyl Blue 636, from
BASF, Parsippany, NJ
PM 259: Solvent Black 46, Sepisol Fast Black
CN, from BIMA, France
5 Resin SK: a ketone/formaldehyde resin, from Huls
America, Rockleigh, NJ
ODEA: oleic diethanolamine, Alkamide DO2805,
from Rhone-Poulenc, Monmolith
10 Junction, NJ

EXAMPLE 1: Blue Inks

Seven blue inks, 9-0 through 9-6, were
prepared, their formulations being shown in
Table 1 below. The viscosity, the coefficient
15 of friction, the laydown and the buildup of each
ink were measured. By "laydown" is meant the
amount of ink deposited on a substrate from a
marking instrument.

The viscosity of an ink was measured
20 at a shear rate of 300 sec^{-1} at room temperature
using a Haake CV-100 Viscometer, made by Haake
Buchler Instruments, Inc. of Saddle Brook, NJ,
using ME-15 sensor system.

The writing friction of a ballpoint
25 pen was measured by a friction tester which used
a Schaevitz force transducer Model No. STD-G-
100, manufactured by Schaevitz Engineering
Corporation, Pennsauken, NJ, to measure
frictional force for a ballpoint sliding on the
30 surface of a sheet of paper. The ballpoint pen
was writing on 60 pound white paper at 22 ft/min
writing speed, 60 degree from horizontal writing
angle and at 200 grams writing load.

"Coefficient of friction" is defined as writing
35 friction divided by writing load.

- 11 -

The laydown of a ballpoint pen is measured by a Hartley Write Test Machine, Model W-10, made by The Hartley Company, Costa Mesa, CA, at 22 ft/min writing speed and 125 grams writing load. "Laydown" is defined as milligrams of ink per 185 feet of written line. "Buildup," on the other hand, is defined as the weight of ink (mg) attached to the tip of the marking instrument at the end of a laydown measurement.

Two different types of ball points, 451 SS point and Flex 474 point, were used to measure the writing friction, laydown and buildup. 451 SS point was made of stainless steel and used 1 mm tungsten carbide ball. Flex 474 point, on the other hand, was made of nickel silver and used 1 mm tungsten carbide ball.

TABLE 1

<u>FORMULATIONS (% by weight)</u>							
	<u>9-0</u>	<u>9-1</u>	<u>9-2</u>	<u>9-3</u>	<u>9-4</u>	<u>9-5</u>	<u>9-6</u>
PM 71	19.8	25.8	25.5	25.6	25.5	25.7	24.8
PM 78	19.8	25.8	25.5	25.5	25.5	25.7	24.8
PM 83	9.9	12.8	12.7	12.7	12.6	12.7	12.3
PM 74	2.0	2.0	2.0	2.0	2.0	2.0	2.0
Resin SK	14.6	0.0	0.7	0.5	0.6	0.0	0.0
PM 81	0.3	0.0	0.0	0.1	0.2	0.3	2.5
PM 21	25.4	25.4	25.4	25.4	25.4	25.4	25.4
PM 24	3.9	3.9	3.9	3.9	3.9	3.9	3.9
PM 25	4.3	4.3	4.3	4.3	4.3	4.3	4.3
Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Vis- cosity ¹	12500	350	380	400	520	460	4800
Coefficient of Friction							
Flex-474	0.16	0.11	0.11	0.11	0.10	0.10	0.13
451SS	0.18	0.14	--	--	--	--	--
Laydown ²							
Flex-474	18.0	20.0	22.2	16.7	15.1	16.2	14.9
451SS	17.1	18.3	--	--	--	--	--
Buildup ³							
Flex-474	0.37	0.47	0.27	0.90	0.13	0.10	0.10
451SS	0.13	0.30	--	--	--	--	--

1. in centipoise or cps

2. in mg/185 ft

3. in mg

- 13 -

As shown in Table 1, the viscosity of the inks was adjusted by changing the amounts of two polymers, PM 81 (i.e., PVP) and Resin SK. The writing friction (which is proportional to the coefficient of friction) was greatly reduced when inks of lower viscosity were used.

Three additional blue inks, 11-1, 11-2 and 11-3, were prepared (see Table 2 below). Like 9-5, 11-1, 11-2 and 11-3 all had a polymer content of 0.3% (i.e., 0.3% PVP). However, 11-1 and 11-2 differed from 9-5 in that they contained 10% and 20% more of each of the dyes (i.e., PM 21, PM 24 and PM 25), respectively. 11-3, on the other hand, contained the same amount of total dyes (i.e., PM 21, PM 24 and PM 25) as 9-5, with a PM 24 content being twice that of 9-5. The viscosity, the coefficient of friction and the buildup and the laydown were measured following the same procedures described above. As shown in Table 2, all three inks gave writing friction which was slightly higher than 9-5.

The line intensity of the three inks was also measured using a light reflectance measuring apparatus, Macbeth PCM II, made by Macbeth Division of Kollmorgen Corp. of Newburgh, NY, with filter A. Line intensity is a measure of the darkness of a written line, in this instance, % reflectance. The lower the value for % reflectance, the darker the line. Absolute black would give a zero % reflectance value. As shown in Table 2, all three inks gave satisfactory line intensity.

Page missing at the time of publication

- 15 -

An additional liquid ink, 13-1, was prepared and various properties thereof were measured and compared with those of 11-39-0 and 11-2 (see Table 3 below). Except for the laydown, other properties were determined following the same procedures described above. The laydown was measured using an ANJA Write Test Machine, W-10 Model B, made by Anja Engineering Corporation of Monrovia, CA at 22 ft/min writing speed and 200 grams writing load.

Note that 13-1 differed from 11-3 only in that it only contained a single dye, PM 71. By contrast, three dyes, PM 71, PM 78 and PM 83, were included in 11-3. Since PM 71 has a viscosity lower than that of PM 78 or PM 83, 13-1 is less viscous than 11-3. As shown in Table 3, 13-1 and 11-3 were very similar in terms of writing friction, buildup, laydown and line intensity. Both inks gave a much lower writing friction than 9-0, a prior art ink.

TABLE 3*

FORMULATIONS (% by weight)

	<u>13-1</u>	<u>11-3</u>	<u>9-0</u>
PM 71	64.1	25.7	19.8
PM 78	0.0	25.7	19.8
PM 83	0.0	12.8	9.9
PM 74	2.0	2.0	2.0
Resin SK	0.0	0.0	14.0
PM 81	0.3	0.3	0.3
PM 21	22.0	22.0	25.4
PM 24	7.9	7.9	3.9
PM 25	3.7	3.7	4.3
Total	100.0	100.0	100.0
Vis- cosity	150	450	12500
Coefficient of Friction†	0.11	0.11	0.16
Buildup†	0.5	0.5	0.4
Laydown†	17.8	16.9	18.0
Line Intensity†			
initial	15.5	16.6	18.3
after 185 ft	14.5	14.8	15.3

* Footnotes 1-3 of Table 1 are applicable here.

† Flex-474 points were used.

- 17 -

EXAMPLE 2: Black Inks

Two black inks, 10-0 and 10-1, were prepared (see Table 4 below). 10-0, a prior art high-viscosity ink, had a polymeric content of 27.2%, i.e., 27% of Resin SK and 0.2% of PM 81 (PVP). By contrast, 10-1 did not contain any polymers. As a result, it had a very low viscosity (60 cps) and gave much lower writing friction than 10-0 using the ballpoint pen Flex-474.

TABLE 4

	<u>FORMULATIONS (% by weight)</u>	
	<u>10-0</u>	<u>10-1</u>
PM 71	17.8	27.9
PM 78	30.3	47.4
PM 74	1.0	1.0
ODEA	27.0	1.0
Resin SK	27.0	0.0
PM 81	0.2	0.0
PM 259	22.7	22.7
Total	100.0	100.0
Viscosity	7500	60
Coefficient of Friction		
Flex-474	0.18	0.11
451SS	0.18	0.18
Buildup		
Flex-474	--	0.17
451SS	0.10	0.23

* Footnotes 1 and 3 of Table 1 are applicable here.

- 19 -

Without further elaboration, it is believed that one skilled in the art can, based on the above working examples and other descriptions herein, utilize the present invention to its fullest extent.

5

OTHER EMBODIMENTS

From the above description, one skilled in the art can easily ascertain the essential characteristics of the present invention, and without departing from the spirit and scope thereof, can make various changes and modifications of the invention to adapt it to various usages and conditions. Thus, other embodiments are also within the claims.

10

- 20 -

C L A I M S

1. A non-erasable liquid ink for a marking instrument comprising a colorant and a solvent, said ink having a water content of about 0-15% by weight and a viscosity of about 15 to 4,500 cps.
2. The ink of claim 1, wherein said ink has a viscosity of about 50 to 2,000 cps.
3. The ink of claim 2, wherein said ink has a viscosity of about 100 to 1,000 cps.
4. The ink of claim 3, wherein said ink has a viscosity of about 150 to 600 cps.
5. The ink of claim 1, 2 or 3, further comprising one or more polymers with molecular weights ranging from about 1×10^4 to 1×10^6 daltons with the total content of said one or more polymers being about 0.05% to 2.5% by weight of said ink.
6. The ink of claim 5, wherein the total content of said one or more polymers is about 0.05% to 1.0% by weight of said ink.
7. The ink of claim 6, wherein the total content of said one or more polymers is about 0.3% by weight of said ink.
8. The ink of claim 4, further comprising one or more polymers with molecular weights ranging from about 1×10^4 to 1×10^6 daltons with the total content of said one or more polymers being about 0.05% to 2.5% by weight of said ink.
9. The ink of claim 8, wherein the total content of said one or more polymers is about 0.05% to 1% by weight of said ink.
10. The ink of claim 9, wherein the total content of said one or more polymers is about 0.3% by weight of said ink.

- 21 -

11. The ink of claim 10, wherein said one or more polymers include polyvinylpyrrolidone.
12. The ink of claim 11, wherein said one or more polymers further include
5 ketone/formaldehyde resin.
13. The ink of claim 10, further comprising a lubricant.
14. The ink of claim 13, wherein said lubricant is oleic acid or oleic diethanolamine.
- 10 15. The ink of claim 10, wherein said colorant is a pigment.
16. The ink of claim 15, further comprising a gelling agent.
- 15 17. A non-erasable liquid ink for a marking instrument comprising one or more polymers with molecular weights ranging from about 1×10^4 to 1×10^6 daltons, a colorant and a solvent, with the total content of said one or more polymers being about 0.05% to 2.5% by
20 weight of said ink and a water content being about 0-15% by weight of said ink.
18. The ink of claim 5, wherein the total content of said one or more polymers is about 0.05% to 1% by weight of said ink.
- 25 19. The ink of claim 6, wherein the total content of said one or more polymers is about 0.3% by weight of said ink.
20. The ink of claim 19, wherein said one or more polymers include polyvinylpyrrolidone.
- 30 21. The ink of claim 20, wherein said one or more polymers further include ketone/formaldehyde resin.
22. The ink of claim 19, further comprising a lubricant.

- 22 -

23. The ink of claim 22, wherein said lubricant is oleic acid or oleic diethanolamine.

24. The ink of claim 19, wherein said colorant is a pigment.

5 25. The ink of claim 24, further comprising a gelling agent.

26. A marking instrument which comprises a body, a reservoir chamber within said body, and a non-erasable liquid ink in said chamber, said
10 ink comprising a colorant and a solvent with a water content of about 0-15% by weight and a viscosity of about 15 to 4,500 cps.

27. The marking instrument of claim 26, wherein said ink has a viscosity of about 50 to
15 2,000 cps.

28. The marking instrument of claim 27, wherein said ink has a viscosity of about 100 to 1,000 cps.

29. The marking instrument of claim 28, wherein said ink has a viscosity of about 150 to
20 600 cps.

30. The marking instrument of claim 29, further comprising one or more polymers with molecular weights ranging from about 1×10^5 to
25 5×10^5 daltons with the total content of said one or more polymers being about 0.05% to 2.5% by weight of said ink.

31. The marking instrument of claim 30, wherein the total content of said one or more
30 polymers is about 0.05% to 1% by weight of said ink.

32. The marking instrument of claim 31, wherein the total content of said one or more polymers is about 0.3% by weight of said ink.

35 33. A marking instrument which comprises a

- 23 -

body, a reservoir chamber within said body, and a non-erasable liquid ink in said chamber, said ink comprising one or more polymers with molecular weights ranging from about 1×10^4 to 1×10^6 daltons, the total content of said one or more polymers being about 0.05% to 2.5% by weight of said ink and a water content of about 0-15% by weight of said ink.

34. The marking instrument of claim 26 or 33, further comprising an ink feed device having a channel for conducting said ink from said chamber to a marking tip, an elastomeric member which partly confines said chamber and supports said feed device with respect to said body, and a valve defined by said feeding device and said elastomeric member for controlling communication between said chamber and said channel, whereby said feed device is retractable relative to said body under a force exerted against said tip, and in response to such retraction said chamber is pressurized by deflection of said elastomeric member and said valve is opened to allow said ink to enter said channel from said chamber.

35. The marking instrument of claim 34, wherein said marking tip is a roller ball.

36. A marking instrument comprising a body, a reservoir chamber within said body, a liquid marking ink in said chamber, an ink feed device having a channel for conducting said ink from said chamber to a marking tip, an elastomeric member which partly confines said chamber and supports said feed device with respect to said body, and a valve defined by said feeding device and said elastomeric member for controlling communication between said

- 24 -

chamber and said channel, whereby said feed device is retractable relative to said body under a force exerted against said tip, and in response to such retraction said chamber is

5 pressurized by deflection of said elastomeric member and said valve is opened to allow said ink to enter said channel from said chamber.

1 / 3




FIG. 1




FIG. 2

SUBSTITUTE SHEET (RULE 26)

2 / 3




FIG. 3




FIG. 4

3 / 3




FIG. 5

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US94/11842

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : CO9D 11/18; CO8L 61/04; B43K 5/00
US CL : 260/Dig. 38; 523/161; 524/509, 510; 401/206, 209
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 260/Dig. 38; 523/161; 524/509, 510; 401/206, 209

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 4,471,079 (ENAMI) 11 September 1984, Column 1, lines 11-64; Column 2, lines 35-61; Column 3, lines 8-64; Column 4, lines 5-44; Column 5, lines 8-59; Column 7, lines 1-68; Column 8, lines 15-63; Column 9, lines 1-59.	1-36
Y	US, A, 4,940,628 (LIN ET AL.) 10 July 1990, Column 3, lines 15-68; Column 4, lines 1-60; Column 5, lines 1-55.	1-25
Y	US, A, 4,391,927 (FARMER, III) 05 July 1983, Column 1, lines 28-65; Column 2, lines 7-57; Column 3, lines 5-51; Column 5, lines 1-40.	1-25

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T	Later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be part of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

10 FEBRUARY 1995

Date of mailing of the international search report

24 MAR 1995

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

PAUL MICHL

Telephone No. (703) 308-2351

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US94/11842

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 4,721,739 (BRENNEMAN ET AL.) 26 January 1988, Column 2, lines 3-65; Column 3, lines 1-59; Column 5, lines 7-58; Column 6, lines 1-55; Column 7, lines 1-65.	1-25
Y	US, A, 4,973,180 (HORI) 27 November 1990, Column 1, lines 46-68; Column 2, lines 1-65; Column 3, lines 1-35; Column 5, lines 1-33.	26-36
Y	US, A, 4,509,876 (HORI) 09 April 1985, see whole document.	26-36